

Merbenit DC25

Merbenit DC25 is an elastic sealant for the caulking of timber panelled deck in ship building. Thanks to SMP base excellent for processing and grinding. Merbenit DC25 is in particular resistant to environmental influences. Meets the requirements of the International Maritime Organisation IMO.

Product advantages

- Compatible with paints
- Simple processing
- High elasticity, good mechanical strength
- Long open time
- Free of solvents, isocyanates and silicones
- Non-corrosive on surfaces
- Vibration absorbing
- Very wide adhesion range
- Very good sealing properties
- Excellent weathering and ageing resistance
- Rapidly grindable

Technical data

Shore A hardness, DIN 53505	30
Modulus elongation at 100%, DIN 53504 S2	ca. 0.6 N/mm ²
Elongation at break, DIN 53504 S2	ca. 600%
Tensile strength, DIN 53504 S2	ca. 1.6 N/mm ²
Consistency	pasty, not stable in vertical joints
Tooling time	max. 15 min.
Curing rate after 24h	≥ 2.5 mm
Curing rate after 48h	≥ 3.5 mm
Density	1.36 ± 0.05 g/cm ³
Volume change, DIN EN ISO 10563	≤ 6%
Temperature resistance after curing	- 40 °C to + 90 °C
Application temperature	+ 5 °C to + 30 °C

All measurements were performed under normal conditions (23 °C and 50 % relative humidity).

Application

Suitable for sealing of teak, pitch pine, oak, sipo etc. Sealing in areas of intense weathering and UV strain. Avoid contact points to non-system adhesives and sealants of other manufacturers. Note: Due to the large number of care products available on the market for teak (which includes teak cleaner, teak oils, etc), we can not furnish a guarantee for incompatibilities that may occur. We recommend to clean the final deck only with seawater and a brush.

Substrate range

Teak, larch, doussie, douglas fir, pitch pine, deck covering of plastic (except polyethylen and polypropylen) on boat plywood, fiberglass, aluminium and steel. Note: The substrate must be free of rust and treated against corrosion.

Meets the standards

- IMO FTPC Parts 2+5

Technical data sheet Merbenit DC25

Substrate preparation

During renovations: Replace defective timber and grind the joint edges. The joints must be free of dirt, dust, oil and grease. Insert a joint tape to avoid a three-sided bonding. Make sure contact points to system strange adhesives and sealants from other manufacturers are avoided. Make sure no direct sunlight affects the deck during the application until Merbenit DC25 is fully cured. The temperature during the application shall be constant or falling.

Adhesion promoter

Because of the high loads affecting a deck joint, a previous treatment of the timber with Adhesion promoter SP is recommended in any case. Adhesion Promoter SP provides an optimal adherence between the timber and Merbenit DC25. In addition, a barrier is created by the adhesion promoter between very oily and resinous timber and the sealant which strongly raises the life span of the joint.

Processing

- Can be applied directly from the cartridge / sausage using a suitable caulking gun (manual, air, battery)
- Cut the nozzle tip according to the joint width
- Merbenit DC25 is filled slightly overflowing into the joints. The overflowing material is smoothed with a spatula. After 2 days the freshly sealed deck can be grinded. Grind in joint direction. Grain of the sandpaper: 80 - 120.

Chemical resistance

- Good against water, aliphatic solvents, oils, grease, diluted inorganic acids and alkalis
- Moderate against esters, ketone and aromatics
- Not resistant against concentrated acids and chlorinated hydrocarbons

Colours

- black
- other colours on request

Packaging

- Cartridges of 290 ml in carton of 12 units
- Sausages of 600 ml in carton of 12 units

Shelf life and storage conditions

- 12 months from date of production
- Store cool and dry
- Further information on request

Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

merz+benteli ag

Freiburgstrasse 616
CH - 3172 Niederwangen
Tel. +41 31 980 48 48
Fax +41 31 980 48 49
info@merz-benteli.ch
www.merz-benteli.ch

As of: 10.02.2016

Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne

