

MOLYKOTE® HP-300 Grease

Fully fluorinated grease provides extraordinary performance under extreme conditions

Features

- Compatible with most plastics
- Excellent stability at high temperatures
- Superior resistance to chemicals and solvents
- Minimal deterioration due to oxidation; appropriate for long-term lubrication
- Low vapor pressure (base oil)

Composition

- Perfluoropolyether
- Fluorinated polymer

Applications

MOLYKOTE® HP-300 Grease can be used broadly under harsh conditions such as low or high temperatures, corrosive, solvent, liquefied natural gasses, high vacuum, etc. It can be used on cleanroom equipment and semiconductor manufacturing equipment where the volatilization of the lubricating material is undesirable.

How to use

Clean point of application. As is usual with lubricating greases, apply or fill by means of a brush, spatula, or automatic lubrication device.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored, unopened, in a cool, dark place, this product has a usable life of 36 months from the date of production.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Appearance		White
JIS K 2220	Penetration (worked 60 times)	mm/10	280
	NLGI class		2
	Service temperature range	°C	-65 to 250
	Density	g/cm ³	2.0
MIL-S-8660	Bleed (200°C, 24 hours)	%	8.0
MIL-S-8660	Evaporation (200°C, 24 hours)	%	0.2
MIL-S-8660	Evaporation (200°C, 1,000 hours)	%	1.0
ASTM D2596	Four ball weld load (1,500 rpm/1 minute)	N	3,300
ASTM D2266	Four ball wear scar (1,200 rpm, 392 N, 1 hour)	mm	1.1
JIS K 2220	Low temperature torque test (-20°C)		
	Starting torque	Ncm	4.1
	Running torque	Ncm	1.8
JIS K 2220	Low temperature torque test (-40°C)		
	Starting torque	Ncm	11
	Running torque	Ncm	3.6
	Base oil vapor pressure 20°C	Pa	4x10 ⁻¹⁰

⁽¹⁾JIS: Japanese Industrial Standard. MIL: Military Specification and Standards. ASTM: American Society for Testing and Materials.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2002-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.