

# Technical Datasheet

## Elecolit<sup>®</sup> 3064



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Product Description

Panacol Elecolit<sup>®</sup> adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Elecolit<sup>®</sup> adhesives are electrically and / or thermally conductive adhesives which are designed for potting, bonding or contacting of conductors.

Elecolit<sup>®</sup> 3064 is a UV and light-curing, one component anisotropic conductive adhesive with good adhesion to PET, Kapton, Mylar and other substrates for the manufacture of flexible circuits. In thin layers, Elecolit<sup>®</sup> 3064 is transparent with a slightly brownish color. Elecolit<sup>®</sup> 3064 is usually applied with pressure / time dosing devices. During the curing process, the pressure (1.2 - 1.7 N / mm<sup>2</sup>) must be applied using a glass punch.

### Curing Properties

UV-A	VIS	Thermal curing	Activator curing
✓	✓	-	-

✓ suitable      - not suitable

The product cures within seconds with radiation in the UV-A - (320 nm - 390 nm) and visible range (405 nm). For rapid and high quality crosslinking we recommend the UV devices manufactured by Dr. Hoenle AG, which complement our adhesive technology.

Bluepoint LED/LED-spot		
Wavelength [nm]	365	405
Suitability	++	+++

+ application-related    ++ well-suited    +++ ideal    - not suitable

To obtain full cure at least one substrate must be transparent to the recommended wavelength. The curing speed will depend on the intensity of light, light source, the exposure time, and the light transmittance of the substrate. Increased mechanical properties are achieved after 12 hours.

UV-curing		
Intensity [mW/cm <sup>2</sup> ]	Layer thickness [mm]	Time [sec]
70	0,5	30

VIS-curing		
Intensity [mW/cm <sup>2</sup> ]	Layer thickness [mm]	Time [sec]
100	0,5	10

### Technical Data

Resin	acrylate
Appearance	transparent
Filler	gold coated particles
Filler – weight [%]	1
Particle size D95 [µm]	10

# Technical Datasheet

## Elecolit<sup>®</sup> 3064



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Uncured material

Viscosity [mPas]	gel-like
Density [g/cm <sup>3</sup> ] <i>PE-Norm 004</i>	1,1
Flash point [°C] <i>PE-Norm 050</i>	>93

### Cured material

Hardness shore D <i>PE-Norm 006</i>	60 - 70
Temperature resistance [°C] <i>PE-Norm 065</i>	-50 - 150
Shrinkage [%] <i>PE-Norm 031</i>	4,3
Water absorption [mass %] <i>PE-Norm 016</i>	<1,5

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	-45,0
Coefficient of linear expansion [ppm/K] below T <sub>g</sub> <i>PE-Norm 017</i>	154,0
Coefficient of linear expansion [ppm/K] above T <sub>g</sub> <i>PE-Norm 017</i>	431,0

Young's modulus E [MPa] <i>PE-Norm 056</i>	1,4
Lap shear strength (glass/glass) [MPa] <i>PE-Norm 013</i>	6,9
Lap shear strength (glass/Al) [MPa] <i>PE-Norm 013</i>	3,4
Lap shear strength (glass/steel) [MPa] <i>PE-Norm 013</i>	2,6
Lap shear strength (PC/PC) [MPa] <i>PE-Norm 013</i>	2,1
Lap shear strength (PC/PMMA) [MPa] <i>PE-Norm 013</i>	2,5
Lap shear strength (PC/FR4) [MPa] <i>PE-Norm 013</i>	2,4

# Technical Datasheet

## Elecolit<sup>®</sup> 3064



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	0°C - 10°C	0°C - 10°C	at delivery min. 3 months max. 6 months
Other packages			

**\*Store in original, unopened containers!**

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP<sup>®</sup> Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

### Note

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2011/65/EU "RoHS II" .

Our data sheets have been compiled to the best of our knowledge. The enclosed information describes characteristic properties, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For any additional technical support, please contact our application engineering department. For warranty claims, please refer to our standard terms and conditions.