

Vitralit 1702 is a very low viscous uv-a curing adhesive with excellent bonding on most plastic materials. It has outstanding qualities for capillar bondings and is known for very low oxygen inhibition.

Vitralit 1702 is released according to USP Class VI and can be used for all sterilization methods customary in the market - especially for Ethoxy- as well as Gamma sterilization.

Shelf life:

Store in original, unopened containers for 6 months at max. 25°C

Technical Data

Color	amber
Resin	acrylat

UNCURED PROPERTIES

Viscosity (Brookfield LVT/25°C) [mPa*s]	PE-Norm P001	70 to 200
Flash point [°C]	PE-Norm P050	> 93
Density [g/cm³]	PE-Norm P051	approx. 1.1
Refractive Index [nD20]	PE-Norm P018	1.4815

Curing

UV(UV-A 60mW/cm² Thickn.st. 0,5mm): [sec.]	PE-Norm P002	15
Full Strength [hours]	PE-Norm P032	12
Depth of Cure [mm]	PE-Norm P033	3

CURED PROPERTIES

Temperature Resistance [°C]	PE-Norm P030	-55 to 135
Hardness Shore D	PE-Norm P052	65 to 75
Water Absorption [Gew-%]	PE-Norm P053	< 5
TG DSC [°C]	PE-Norm P009	45 to 55
Dielectric Strength [kV/mm]	PE-Norm P055	0,5

Our data sheets have been compiled to the best of our knowledge. The information included in our data sheets is exclusive information for the intended user and describes characteristics, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For an additional technical consultation, please contact our RD department. In general, for guarantee claims, please refer to our standard terms and conditions.

Adhesives
and more...

Adhesives
and more...

Instructions for Use

Surface Preparation

The surfaces to be adhered should be free of dust, oil, fat or any other dirt in order to optimise reproducible bonds. Lightly soiled surfaces can be cleaned with cleaner IP, whereas substrates with low surface energy (such as polyethylene, polypropylene or Teflon) need to be treated physically using plasma or corona to create a suitable working surface. For glass bonding applications we have developed a special primer pen which can be easily applied to prepare the surface for best results.

Application

Our products are delivered ready for use. As soon as you receive them, you can dispense them, be it by hand from the container, or semi/fully automatically. When applied automatically, we recommend the use of air pressure with the appropriate cartridge/piston combination to dispense the adhesive at the required speed and accuracy. If help is required, please consult our engineering department

Please read the corresponding **Safety Data Sheet** for this product.